



(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:  
**06.02.2002 Bulletin 2002/06**

(51) Int Cl.<sup>7</sup>: **A61L 27/36, A61L 27/40**

(21) Application number: **01306559.4**

(22) Date of filing: **31.07.2001**

(84) Designated Contracting States:  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU**  
**MC NL PT SE TR**  
Designated Extension States:  
**AL LT LV MK RO SI**

(30) Priority: **04.08.2000 US 223399 P**

(71) Applicant: **DEPUY ORTHOPAEDICS, INC.**  
**Warsaw, Indiana 46581-0988 (US)**

(72) Inventors:  
• **Plouhar, Pamela L.**  
**South Bend, IN 46614 (US)**

- **Malaviya, Prasanna**  
**Ft Wayne, IN 46804 (US)**
- **Ferguson, Joe W.**  
**Warsaw, IN 46582 (US)**
- **Melican, Mora C.**  
**Bridgewater, NJ 08807 (US)**

(74) Representative: **Belcher, Simon James**  
**Urquhart-Dykes & Lord Tower House Merrion**  
**Way**  
**Leeds LS2 8PA (GB)**

(54) **Reinforced small intestinal submucosa**

(57) A bioprosthetic device [10] is provided for soft tissue attachment, reinforcement, and or reconstruction. The device comprises a naturally occurring extracellular matrix portion [12] and a synthetic portion [14]. In illustrated embodiments, the naturally occurring extracellular matrix portion comprises layers [16, 18] of

small intestine submucosa, and the synthetic portion comprises one or more rows [26] of fibers [28] or mesh [320] positioned between layers of the small intestine submucosa.

**Description**Field of the Invention

5 **[0001]** The present invention relates to bioprosthetics and particularly to the use of bioprosthetics for the repair and replacement of connective tissue. More particularly, the present invention relates to the use of a composite bioprosthetic device made up of a synthetic portion and heterologous animal tissue.

Background and Summary of the Invention

10

**[0002]** Currently there are multiple patents and publications that describe in detail the characteristics and properties of small intestine submucosa (SIS). See, for example, U.S. Patent Nos. 4,352,463, 4,902,508, 4,956,178, 5,281,422, 5,372,821, 5,445,833, 5,516,533, 5,573,784, 5,641,518, 5,645,860, 5,668,288, 5,695,998, 5,711,969, 5,730,933, 5,733,868, 5,753,267, 5,755,791, 5,762,966, 5,788,625, 5,866,414, 5,885,619, 5,922,028, 6,056,777, and WO 97/37613. SIS, in various forms, is commercially available from Cook Biotech Incorporated (Bloomington, IN). Further, U.S. Patent No. 4,400,833 to Kurland and PCT publication having International Publication Number WO 00/16822 provide information related to bioprosthetics.

15

**[0003]** There are currently many ways in which various types of soft tissues such as ligaments or tendons, for example, are reinforced and/or reconstructed. Suturing the torn or ruptured ends of the tissue is one method of attempting to restore function to the injured tissue. Sutures may also be reinforced through the use of synthetic non-bioabsorbable or bioabsorbable materials. Autografting, where tissue is taken from another site on the patient's body, is another means of soft tissue reconstruction. Yet another means of repair or reconstruction can be achieved through allografting, where tissue from a donor of the same species is used. Still another means of repair or reconstruction of soft tissue is through xenografting in which tissue from a donor of a different species is used.

20

**[0004]** According to the present invention, a bioprosthetic device for soft tissue attachment, reinforcement, and/or reconstruction is provided. The bioprosthetic device comprises a small intestinal submucosa (SIS) or other naturally occurring extracellular matrix (ECM), formed to include a tissue layer of SIS, and a synthetic portion coupled to the SIS tissue layer. The tissue layer of SIS may also be dehydrated.

25

**[0005]** In preferred embodiments, the SIS portion of the bioprosthetic device includes a top tissue layer of SIS material and a bottom tissue layer of SIS material coupled to the top tissue layer. The synthetic portion of the bioprosthetic device includes a row of fibers positioned to lie between the top and bottom tissue layers of the SIS portion. The fibers are positioned to lie in a spaced-apart coplanar relation to one another along a length, L, of the SIS portion. The fibers are each formed to include a length L2, where L2 is longer than L so that an outer end portion of each fiber extends beyond the SIS portion in order to anchor the bioprosthetic device to the surrounding soft tissue.

30

**[0006]** In other embodiments, the synthetic portion of the bioprosthetic device includes a mesh member formed to define the same length, L, as the SIS portion. In yet another embodiment, the synthetic portion of the bioprosthetic device includes a mesh member having a body portion coupled to the SIS portion and outer wing members coupled to the body portion and positioned to extend beyond the length, L, and a width, W, of the SIS portion in order to provide more material for anchoring the bioprosthetic device to the surrounding soft tissue.

35

**[0007]** SIS is intended to identify small intestine submucosa. While porcine SIS is widely used, it will be appreciated that small intestine submucosa may be obtained from other animal sources, including cattle, sheep, and other warm-blooded mammals. Further, other sources of extracellular matrices from various tissues are known to be effective for tissue remodeling as well. These sources include, but are not limited to, stomach, bladder, alimentary, respiratory, and genital submucosa. See, e.g., U.S. Patent Nos. 6,171,344, 6,099,567, and 5,554,389. Such submucosa-derived matrices comprise highly conserved collagens, glycoproteins, proteoglycans, and glycosaminoglycans. Additionally, other ECMs are known, for example lamina propria and stratum compactum.

40

**[0008]** For the purposes of this invention, it is within the definition of a naturally occurring ECM to clean, delaminate, and/or comminute the ECM, or even to cross-link the collagen fibers within the ECM. However, it is not within the definition of a naturally occurring ECM to extract and purify the natural fibers and refabricate a matrix material from purified natural fibers. Compare WO 00/16822 A1. Thus, while reference is made to SIS, it is understood that other naturally occurring ECMs are within the scope of this invention.

50

**[0009]** Fiber is intended to identify a synthetic reinforcement component present within the implant to contribute enhanced mechanical and handling properties. The reinforcement component is preferably in the form of a braided suture or a mesh fabric that is biocompatible. The reinforcement component may be bioabsorbable as well.

55

**[0010]** The reinforcing component of the tissue implant of the present invention may be comprised of any absorbable or non-absorbable biocompatible material, including textiles with woven, knitted, warped knitted (i.e., lace-like), non-woven, and braided structures. In an exemplary embodiment the reinforcing component has a mesh-like structure. In any of the above structures, mechanical properties of the material can be altered by changing the density or texture

of the material. The fibers used to make the reinforcing component can be, for example, monofilaments, yarns, threads, braids, or bundles of fibers. These fibers can be made of any biocompatible material, including bioabsorbable materials such as polylactic acid (PLA), polyglycolic acid (PGA), polycaprolactone (PCL), polydioxanone (PDO), trimethylene carbonate (TMC), polyvinyl alcohol (PVA), and copolymers or blends thereof. In an exemplary embodiment, the fibers that comprise the mesh are formed of a polylactic acid and polyglycolic acid copolymer at a 95:5 mole ratio.

**[0011]** Additional features of the present invention will become apparent to those skilled in the art upon consideration of the following description of preferred embodiments of the invention exemplifying the best mode of carrying out the invention as presently perceived.

#### Brief Description of the Drawings

**[0012]** The detailed description particularly refers to the accompanying figures in which:

Fig. 1 is a perspective view showing a composite bioprosthetic device of the present invention formed to include a small intestinal submucosa (SIS) portion and a synthetic portion and showing the SIS portion including a top tissue layer of SIS material and a bottom tissue layer of SIS material and further showing the synthetic portion including a row of four fibers positioned to lie in coplanar relation to each other between the top and bottom tissue layers of the SIS portion and positioned to run longitudinally along a length of the SIS portion and extend beyond a first and second end of the SIS portion in order to anchor the bioprosthetic device to surrounding soft tissue;

Fig. 2 is a perspective view similar to Fig. 1 showing an SIS portion of another bioprosthetic device of the present invention being formed to include a top layer, a bottom layer, and two middle layers positioned to lie between the top and the bottom layers and a synthetic device being formed to include three rows of four fibers so that each row is positioned to lie between each of the adjacent tissue layers of the SIS portion so that each fiber is positioned to run longitudinally along a length, L, of the SIS portion;

Fig. 3 is a sectional view taken along line 3-3 of Fig. 2 showing the top, bottom, and middle tissue layers of the SIS portion and also showing the three rows of fibers of the synthetic portion of the bioprosthetic device;

Fig. 4 is a perspective view showing an SIS portion of yet another bioprosthetic device of the present invention being formed to include four tissue layers, similar to Fig. 2, and also showing a synthetic portion of the bioprosthetic device including a first row of multiple fibers positioned to lie between two tissue layers of the SIS portion along a length, L, of the SIS portion and a second row of multiple fibers positioned to lie between two other tissue layers of the SIS portion along a width, W, of the SIS portion;

Fig. 5 is an exploded perspective view of another bioprosthetic device of the present invention showing an SIS portion of the prosthetic device including top, bottom, and middle tissue layers and showing a synthetic portion including a first and a second mesh member positioned to lie between the top and middle tissue layers of and the middle and bottom tissue layers of the SIS portion, respectively;

Fig. 6 is a sectional view of the bioprosthetic device of Fig. 5 showing first and second mesh members "sandwiched" between the tissue layers of the SIS portion of the device;

Fig. 7 is a perspective view showing an SIS portion of another bioprosthetic device being formed to include a top and a bottom tissue layer and further showing a synthetic portion being formed to include a mesh member having a body portion positioned to lie between the top and bottom tissue layers and outer wing portions provided for anchoring the device to surrounding soft tissue; and

Fig. 8 is a perspective view showing an SIS portion of yet another bioprosthetic device being formed to include a circularly shaped top and bottom tissue layers each having a diameter, D1, and further showing a synthetic portion of the device being formed to include a circular mesh member positioned to lie between the top and bottom tissue layers and having a diameter, D2, which is larger than D1 so that an outer rim portion of the mesh member is formed to extend beyond the top and bottom tissue layers for anchoring the bioprosthetic device to the host tissue during surgery.

#### Detailed Description of the Drawings

**[0013]** A composite bioprosthetic device 10, as shown in Fig. 1, is provided for the purposes of soft tissue attachment, reinforcement, and/or reconstruction. Bioprosthetic device 10 includes a small intestinal submucosa (SIS) portion 12 and a synthetic portion 14. SIS portion 12 is provided to be absorbed into the body and replaced by host tissue. SIS portion 12 acts as a scaffold for tissue ingrowth and remodeling. Synthetic portion 14 of bioprosthetic device 10 provides additional initial mechanical strength to bioprosthetic device 10. Because device 10 includes SIS portion 12 and synthetic portion 14, bioprosthetic device 10 is provided with a differential in biodegradation and bioremodeling rates. Synthetic portion 14, for example, can be configured to degrade at a slower rate than SIS portion 12. Further, synthetic portion 14 may act as an anchor to couple bioprosthetic device 10 to the surrounding soft tissue (not shown) during

surgery.

**[0014]** SIS portion 12 of bioprosthetic device 10, as shown in Fig. 1, includes a top tissue layer 16 and a bottom tissue layer 18 coupled to top tissue layer 16 through a dehydration process. Although top and bottom tissue layers 16, 18 are provided in bioprosthetic device 10 shown in Fig. 1, it is within the scope of this disclosure, as will be described in more detail later, to include SIS portions 12 having any number of tissue layers. It is also included within the scope of this disclosure to provide perforated tissue layers or any other physical configuration of SIS. See Figs. 2-4, for example. Further, it is within the scope of this disclosure to define top and bottom tissue layers 16, 18 as including multiple tissue layers each. In preferred embodiments, for example, top and bottom tissue layers 16, 18 each include three to four layers of SIS tissue. SIS portion 12 further includes a first end 20, a second end 22 spaced-apart from first end 20, and sides 24 coupled to and positioned to lie between first and second ends 20, 22. A length, L, is defined as the distance between first end 20 and second end 22 and a width, W, is defined as the distance between sides 24.

**[0015]** Synthetic portion 14 of bioprosthetic device 10 includes row 26 of four fibers 28, as shown in Fig. 1. Fibers 28 are positioned to lie along length L between top and bottom tissue layers 16, 18 and are further positioned to lie in coplanar relation to one another. When making bioprosthetic device 10, fibers 28 of synthetic portion 14 are placed between top and bottom tissue layers 16, 18 prior to dehydration. Although row 26 of four fibers 28 is provided in bioprosthetic device 10 shown in Fig. 1, it is within the scope of this disclosure to include synthetic portions 14 formed to include any number of rows 26 having any number of fibers 28. It is further within the scope of this disclosure to include fibers 28 made from bioabsorbable and non-bioabsorbable materials. For example, it is within the scope of this disclosure to include fibers 28 made from polylactic acid (PLA) or polyglycolic (PGA) acid, a combination of the two, Panacryl™ absorbable suture (Ethicon, Inc, Somerville, NJ), other bioabsorbable materials, nylon, polyethylene, Kevlar™, Dacron™, PTFE, carbon fiber, or other non-bioabsorbable materials.

**[0016]** As shown in Fig. 1, each fiber 28 of bioprosthetic device 10 includes two outer end portions 30 a middle portion 32 coupled to and positioned to lie between outer end portions 30. Middle portion 32 is positioned to lie between top tissue layer 16 and bottom tissue layer 18 of SIS portion 12. Middle portion 32 of fibers 28 helps to provide strength along length, L, of bioprosthetic device 10. One or more outer end portions 30 of fibers 28 can be used for anchoring bioprosthetic device 10 to surrounding soft tissue (not shown). The combination of SIS portion 12 and fibers 28 further provide bioprosthetic device 10 with differential biodegradation rates. For example, fibers 28 of synthetic portion 14 can be made to be non-bioabsorbable or can be made with material that absorbs into the body at a slower rate than SIS portion 12. Uses for bioprosthetic device 10 shown in Fig. 1 include, but are not limited to, ligament or tendon repair.

**[0017]** An alternate bioprosthetic device 110 is shown in Figs. 2 and 3. Bioprosthetic device 110 include an alternate SIS portion 112 of having top tissue layer 16, bottom tissue layer 18, and two middle tissue layers 115. Top, bottom, and middle tissue layers 16, 18, 115 include one or more layers of SIS tissue each. SIS portion 112, similar to SIS portion 12, also includes a first end 20, a second end 22 spaced-apart from first end 20, and sides 24. Bioprosthetic device 110 further includes an alternate synthetic portion 114 having three rows 26 of four fibers 28. One row 26 is positioned to lie between top tissue layer 16 and one of the middle tissue layers 115. Another row 26 is positioned to lie between the two middle tissue layers 115, and the final row 26 of fibers 28 is positioned to lie between another one of the middle tissue layers 115 and bottom tissue layer 16, as shown in Fig. 3. Fibers 28 of bioprosthetic device 110, similar to fibers 28 of bioprosthetic device 10, are positioned to lie along length, L, of SIS portion 112.

**[0018]** Although fibers 28 of bioprosthetic devices 10, 110 are positioned to lie along length, L, of each respective SIS portion 12, 112, it is within the scope of this disclosure to include a synthetic portion 214 of an alternate bioprosthetic device 210, as shown in Fig. 4, having multi-directional fibers 28 positioned to lie along a length, L, of an SIS portion 212 and along width, W, of SIS portion 212. Synthetic portion 214 of bioprosthetic device 210 includes a first row 226 having seventeen fibers 28 positioned to lie along length, L, of SIS portion 212. Synthetic portion 214 further includes a second row 227 having eighteen fibers 28 positioned to lie along width, W, of SIS portion 212 so that the fibers 28 of first row 226 and second row 227 are positioned to lie orthogonally with respect to each other. Although rows 226 and 227 are positioned to lie in orthogonal relation to one another, it is within the scope of this disclosure to include synthetic portion 214 having first and second rows 226 and 227 that lie at any angular relation to one another. It is also within the scope of this disclosure to include rows 226 and 227 each having any number of fibers 28.

**[0019]** Similar to bioprosthetic device 110 shown in Fig. 2, bioprosthetic device 210 includes a top tissue layer 216, a bottom tissue layer 218, and two middle tissue layers 215, positioned to lie between top and bottom tissue layers 216, 218. As mentioned before, top, bottom, and middle tissue layers 216, 218, 215 are each formed to include one or more layers of SIS tissue. Although SIS portion 212 of bioprosthetic device 210 is shown to include four tissue layers, it is within the scope of the disclosure to include bioprosthetic device 210 having any number of tissue layers. As shown in Fig. 4, first row 226 is positioned to lie between top tissue layer 216 and one of the two middle tissue layers 215 positioned to lie adjacent to top tissue layer 216. Second row 227 is positioned to lie between the other middle tissue layer 215 and bottom tissue layer 218. It is within the scope of this disclosure, however, to include rows 226, 227 positioned to lie between any tissue layer of device 210.

**[0020]** Yet another bioprosthetic device 310 is shown in Figs. 5 and 6. Bioprosthetic device 310 is similar to devices, 10, 110, and 210 and includes an SIS portion 312 having a top tissue layer 316, a bottom tissue layer 318, and a middle tissue layer 315 positioned to lie between top and bottom tissue layers 316, 318. Top, bottom, and middle tissue layers 316, 318, 315 each include one or more layers of SIS tissue. Bioprosthetic device 310 further includes a synthetic portion 314 including first mesh member 320 and second mesh member 322. It is within the scope of this disclosure to include any type of synthetic mesh member. For example, bioabsorbable and/or non-bioabsorbable mesh members 320, 322 made of either woven or nonwoven PGA and/or PLA mixtures are included within the scope of disclosure of this invention. First mesh member 320 is coupled to and positioned to lie between top tissue layer 316 and middle tissue layer 315 and second mesh member 322 is coupled to and positioned to lie between middle tissue layer 315 and bottom tissue layer 318, as shown in Figs. 5 and 6. As shown, each of the first and second mesh members 320, 322 has a length, L, and a width, W, approximately equal to length, L, and width, W, of tissue layers 315, 316, 318, of SIS portion 312. However, in some embodiments, it may be preferable for the mesh to be slightly smaller.

**[0021]** In Fig. 5, second mesh member 322 is shown partially coated in comminuted SIS 340. Comminuted SIS may be used to fill the interstices of second mesh member 322 to provide a stronger device. Other means for reinforcing bioprosthetic device 10 may be employed, including suturing or tacking the various layers together. Further, while comminuted SIS is discussed with respect to the embodiment shown in Fig. 5, it is understood that comminuted SIS may be used to coat the mesh or fibers for any embodiment.

**[0022]** Another embodiment of the present invention includes a bioprosthetic device 410 having a synthetic portion 414 including a mesh member 420, as shown in Fig. 7. Similar to the previously mentioned devices, bioprosthetic device 410 includes an SIS portion 412 having a top tissue layer 416 and a bottom tissue layer 418 coupled to top tissue layer 416. Top and bottom tissue layers 416, 418 each include one or more layers of SIS tissue. Mesh member 420 includes a central body portion (not shown) and outer wing portions 430, as shown in Fig. 7. Outer wing portions 430 are extensions of the central body portion. Although four outer wing portions 430 are shown in Fig. 7, it is within the scope of this disclosure to include a mesh member having a body portion and any number of wing portions 430 coupled to the body portion. The central body portion of mesh member 420 is formed to include a length and a width equal to length, L, and width, W, of SIS portion 412. The central body portion is coupled to and positioned to lie between top tissue layer 416 and bottom tissue layer 418 of SIS portion 412. Each wing portion 430 is coupled to the central body portion of mesh member 420 and is positioned to extend beyond the length, L, and width, W, of SIS portion 412, as shown in Fig. 7. As mentioned before, outer wing portions 430 are extensions of the central body portion. Wing portions 430 provide additional material for anchoring bioprosthetic device 410 to the surrounding soft tissue. Because outer wing portions 430 extend beyond central body portion of mesh member 420, mesh member 420 has a length and a width greater than length, L, and width, W, of SIS portion 412.

**[0023]** Yet another embodiment of the present invention is shown in Fig. 8 showing a bioprosthetic device 510 similar to bioprosthetic device 410, described above. Bioprosthetic device 510 includes an SIS portion 512 and a synthetic portion 514 coupled to SIS portion 512. SIS portion 512 includes a top tissue layer 516 which is circular in shape and a bottom tissue layer 518 which is also circular in shape. Each of the top and bottom tissue layers 516, 518 include one or more layers of SIS tissue. Top and bottom tissue layers 516, 518 each have a diameter, D1. The synthetic portion 514 of bioprosthetic device 510 includes a mesh member 520 coupled to and positioned to lie between top and bottom tissue layers 516, 518. Mesh member 520 is circular in shape and has a diameter, D2, which is greater than diameter, D1, of synthetic portion 512. Therefore, as shown in Fig. 8, an outer rim portion 530 of mesh member 520 is provided. Similar to outer wing portions 430 of bioprosthetic device 410, shown in Fig. 7, outer rim portion 530 of bioprosthetic device 510 provides additional material for anchoring bioprosthetic device 510 to the surrounding soft tissue during surgery.

**[0024]** Although various embodiments have been described in detail above, it is within the scope of this disclosure to include any bioprosthetic device having an SIS portion and a synthetic portion coupled to the SIS portion in order to provide improved initial mechanical strength of the bioprosthetic device, to obtain desired differential biodegradation and bioremodeling rates, and to provide improved anchoring means of the device to the host tissue. For example, Fig. 1-8 show the SIS portion including SIS tissue layers in the form of sheets. It is within the scope of this disclosure, however, to further define the SIS portion to include sheets, perforated sheets, or any other physical configuration of SIS. It is also within the scope of this disclosure to include the synthetic portion comprising Prolene™ (Ethicon, Inc, Somerville, NJ) meshes and/or sutures, Vicryl™ (Ethicon, Inc, Somerville, NJ) meshes and/or sutures, Mersilene™ (Ethicon, Inc, Somerville, NJ) meshes, PDS II™ (Ethicon, Inc., Somerville, NJ) meshes or sutures, Panacryl™ (Ethicon, Inc., Somerville, NJ) meshes or sutures, and Monocryl™ meshes or sutures, for example. Further it is within the scope of this disclosure to include any bioprosthetic devices where the SIS portion includes any number of tissue layers made from SIS and where multiple tissue layers are positioned to lie between each layer of fibers and/or mesh of the synthetic portion. The SIS layers may be dehydrated prior to or subsequent to assembly of the device.

**[0025]** It is also within the scope of this disclosure to include bioprosthetic device where the synthetic portion is either bioabsorbable or non-bioabsorbable and includes any number of fibers and/or any number of mesh members, as

described above. Although Figs. 1-4 show the synthetic portion being defined by fibers, it is within the scope of the disclosure for the synthetic portion to also be defined by fibers or fibrous materials, for example. Further, any shape and/or orientation of the SIS portion and the synthetic portion of the bioprosthetic device is within the scope of this disclosure; Figs. 1-8 are merely examples of various embodiments of the present invention.

#### Example 1

**[0026]** Sheets of clean, disinfected porcine SIS material were obtained as described in U.S. Patent Nos. 4,902,508 and 4,956,178. Ten strips 3.5 inches wide and 6 inches long were cut. The strips were hydrated by placing in RO water, at room temperature, for 5 minutes.

**[0027]** To assemble the implant, five SIS strips were placed on top of each other, while ensuring no air bubbles were trapped between the strips. A knitted Panacryl™ mesh 2 inches wide and 5 inches long, was placed centrally on the 5-layer thick SIS strip. The mesh had been pretreated to remove any traces of oil or other contaminants due to handling. This was done by a series of rinses, each 2 minutes long, in 100%, 90%, 80%, 70% ethanol (200 proof) in RO water, followed by a final 5 minute in RO water. Subsequently, a second 5-layer thick strip of SIS was assembled and placed to sandwich the mesh between the two SIS strips.

**[0028]** The implant was dried under vacuum pressure using a gel drier system (Model FB-GD-45, Fisher Scientific, Pittsburgh, PA) for 3 hours. The gel drier bed temperature was set at 30°C for the procedure. This drying procedure results in "squeezing out" of the bulk water in the implant and also reduces the amount of bound water within the tissue, resulting in a final moisture of between 7%-8%. This process also results in a physical crosslinking between the laminates of SIS and between the mesh and adjacent SIS laminates.

**[0029]** Non-reinforced SIS strips were made in the same way as described, except that no mesh material was placed between the strips of SIS.

#### Example 2

**[0030]** A soaking test was performed to test resistance to delamination. Implants made as specified in Example 1 (both reinforced and non-reinforced) were cut into several strips 1 cm wide by 5 cm long, using a #10 scalpel blade. The strips were immersed in RO water, at room temperature for 1, 2, 5, 10, 20, 30, or 60 minutes. Delamination was detected at the edges of the implants by direct visual observation. All implants showed obvious signs of delamination at 1 hour. In non-reinforced implants, delamination was first visually observed between 40-60 minutes, whereas in the reinforced samples delamination was apparent between 20-30 minutes.

#### Example 3

**[0031]** This example illustrates the enhanced mechanical properties of a construct reinforced with absorbable mesh. Preparation of three-dimensional elastomeric tissue implants with and without a reinforcement in the form of a biodegradable mesh are described. While a foam is used for the elastomeric tissue in this example, it is expected that similar results will be achieved with an ECM and a biodegradable mesh.

**[0032]** A solution of the polymer to be lyophilized to form the foam component was prepared in a four step process. A 95/5 weight ratio solution of 1,4-dioxane/(40/60 PCL/PLA) was made and poured into a flask. The flask was placed in a water bath, stirring at 70°C for 5 hrs. The solution was filtered using an extraction thimble, extra coarse porosity, type ASTM 170-220 (EC) and stored in flasks.

**[0033]** Reinforcing mesh materials formed of a 90/10 copolymer of polyglycolic/poly(lactic acid) (PGA/PLA) knitted (Code VKM-M) and woven (Code VWM-M), both sold under the tradename VICRYL were rendered flat by ironing, using a compression molder at 80 °C/2 min. After preparing the meshes, 0.8-mm shims were placed at each end of a 15.3 x15.3 cm aluminum mold, and the mesh was sized (14.2 mm) to fit the mold. The mesh was then laid into the mold, covering both shims. A clamping block was then placed on the top of the mesh and the shim such that the block was clamped properly to ensure that the mesh had a uniform height in the mold. Another clamping block was then placed at the other end, slightly stretching the mesh to keep it even and flat.

**[0034]** As the polymer solution was added to the mold, the mold was tilted to about a 5 degree angle so that one of the non-clamping sides was higher than the other. Approximately 60 ml of the polymer solution was slowly transferred into the mold, ensuring that the solution was well dispersed in the mold. The mold was then placed on a shelf in a Virtis (Gardiner, NY), Freeze Mobile G freeze dryer. The following freeze drying sequence was used: 1) 20°C for 15 minutes; 2) -5°C for 120 minutes; 3) -5°C for 90 minutes under vacuum 100 milliTor; 4) 5°C for 90 minutes under vacuum 100 milliTor; 5) 20°C for 90 minutes under vacuum 100 milliTor. The mold assembly was then removed from the freezer and placed in a nitrogen box overnight. Following the completion of this process the resulting implant was carefully peeled out of the mold in the form of a foam/mesh sheet.

[0035] Nonreinforced foams were also fabricated. To obtain non-reinforced foams, however, the steps regarding the insertion of the mesh into the mold were not performed. The lyophilization steps above were followed.

#### Example 4

[0036] Lyophilized 40/60 polycaprolactone/polylactic acid, (PCL/PLA) foam, as well as the same foam reinforced with an embedded VICRYL knitted mesh, were fabricated as described in Example 3. These reinforced implants were tested for suture pull-out strength and compared to non-reinforced foam prepared following the procedure of Example 3.

[0037] For the suture pull-out strength test, the dimensions of the specimens were approximately 5 cm X 9 cm. Specimens were tested for pull-out strength in the wale direction of the mesh (knitting machine axis). A size 0 polypropylene monofilament suture (Code 8834H), sold under the tradename PROLENE (by Ethicon, Inc., Somerville, NJ) was passed through the mesh 6.25 mm from the edge of the specimens. The ends of the suture were clamped into the upper jaw and the mesh or the reinforced foam was clamped into the lower jaw of an Instron model 4501 (Canton, MA). The Instron machine, with a 201b load cell, was activated using a cross-head speed of 2.54 cm per minute. The ends of the suture were pulled at a constant rate until failure occurred. The peak load (lbs.) experienced during the pulling was recorded.

[0038] The results of this test are shown below in Table 1.

Table 1:

Suture Pull-Out Data (lbs.)			
Time	Foam	Mesh	Foamed Mesh
0 Day	0.46	5.3 +/- 0.8	5.7 +/-0.3
7 Day*	-	4.0 +/-1.0	5.0 +/-0.5

\* exposed for 7 days to phosphate buffered saline at 37°C in a temperature controlled water bath.

[0039] These data show that a reinforced foam has improved pull-out strength verses either foam or mesh alone.

[0040] Although the invention has been described in detail with reference to certain preferred embodiments, variations and modifications exist within the scope and spirit of the invention as described and defined in the following claims.

#### Claims

1. A bioprosthetic device for soft tissue attachment, reinforcement, and/or reconstruction, the device comprising  
a naturally occurring extracellular matrix portion, and  
a synthetic portion coupled to the collagen matrix portion.
2. The bioprosthetic device of claim 1, wherein the naturally occurring extracellular matrix portion of claim 1 is an SIS portion.
3. The bioprosthetic device of claim 2, wherein the SIS portion is dehydrated and is formed to include a top tissue layer of SIS coupled to a bottom tissue layer of SIS and the synthetic portion is coupled to and positioned to lie between the top tissue layer and the bottom tissue layer.
4. The bioprosthetic device of claim 3, wherein the synthetic portion includes at least one mesh member.
5. The bioprosthetic device of claim 4, wherein the mesh member includes a length, L1, and a width, W1, equal to or greater than a length, L2, and a width, W2, of the SIS portion.
6. The bioprosthetic device of claim 4, wherein the SIS portion is circular in shape and defines a diameter, D1, and the mesh member is circular in shape and defines a diameter, D2, and further wherein D2 is greater than D1.
7. The bioprosthetic device of claim 3, wherein the synthetic portion includes a row of fibers positioned to lie in coplanar relation to one another along a length, L, of the SIS portion and a row of fibers positioned to lie in coplanar relation to one another along a width, W, of the SIS portion.

8. The bioprosthetic device of claim 3, wherein the synthetic portion includes at least one fiber positioned to lie along a length, L, of the SIS portion.
- 5 9. The bioprosthetic device of claim 8, wherein the fiber includes outer end portions and a middle portion coupled to and positioned to lie between the outer end portions so that the middle portion of the fiber is positioned to lie between the top and the bottom tissue layers of the SIS portion and the outer end portions of the fiber are positioned to extend beyond the length, L, of the SIS portion.
- 10 10. The bioprosthetic device of claim 2, wherein the SIS portion includes multiple sections of SIS each separated by the synthetic portion and wherein each section of SIS includes multiple layers of SIS tissue.
11. The bioprosthetic device of claim 10, wherein the synthetic portion includes a mesh member coupled to at least one section of SIS.
- 15 12. The bioprosthetic device of claim 11, wherein the mesh member has a surface area larger than a surface area of the synthetic portion.
13. The bioprosthetic device of claim 2,  
20 wherein the SIS portion is dehydrated and includes a first end, a second end positioned to lie in spaced-apart relation to the first end, and opposite sides each coupled to and positioned to lie between the first end and the second end, and  
wherein the synthetic device comprises a fiber, the fiber including outer end portions and a middle portion coupled to and positioned to lie between the outer end portions so that the middle portion is coupled to the  
25 SIS portion and the outer portions are positioned to extend beyond the first and second ends of the SIS portion and are formed to anchor the bioprosthetic device to the soft tissue.
14. The bioprosthetic device of claim 2, wherein the synthetic portion includes a mesh member.
- 30 15. The bioprosthetic device of claim 14, wherein the mesh member is coated with comminuted SIS.
16. The bioprosthetic device of claim 15, wherein the mesh member is bioabsorbable.
- 35 17. The bioprosthetic device of claim 15, wherein the SIS portion is dehydrated and defines a length, L, and a width, W, and the mesh member defines the same length, L, and width, W.
18. The bioprosthetic device of claim 16, wherein the SIS portion defines a length, L, and a width, W, and the mesh member includes a central body portion having the length, L, and the width, W, and outer wing members coupled to the body portion and positioned to extend beyond length, L, and width, W, of the SIS portion.
- 40 19. The bioprosthetic device of claim 14, wherein the mesh is smaller than the SIS portion.
20. The bioprosthetic device of claim 16, wherein the SIS portion is circular in shape and defines a diameter, D1, and the mesh member is circular in shape and defines a diameter, D2, and wherein D2 is greater than D1.
- 45 21. The bioprosthetic device of claim 16, wherein the SIS portion defines a length and a width and the mesh portion defines a length and a width greater than the length and width of the SIS portion.
22. The bioprosthetic device of claim 14, wherein the SIS portion is circular and defines a diameter and the mesh  
50 portion is circular and defines a diameter greater than the diameter of the SIS portion.
23. The bioprosthetic device of claim 2, wherein the synthetic portion further includes a row of fibers positioned to lie in spaced-apart, coplanar relation to one another.
- 55 24. The bioprosthetic device of claim 23, wherein the fibers are bioabsorbable.
25. The bioprosthetic device of claim 23, wherein the fibers are non-bioabsorbable.



**EP 1 177 800 A1**

26. The bioprosthetic device of claim 24, wherein the rate of absorption of the fibers is slower than the rate of absorption of the SIS portion.

27. The bioprosthetic device of claim 2, further comprising means for reinforcing the bioprosthetic device.

28. The bioprosthetic device of claim 27, wherein the means for reinforcing the bioprosthetic device comprise a layer of comminuted SIS coating the synthetic device.


29. The bioprosthetic device of claim 1, wherein the synthetic portion comprises a material selected from the group consisting of Prolene™, Vicryl™, Mersilene™, PDS II™, Panacryl™, and Monocryl™.



30. The bioprosthetic device of claim 29, wherein the synthetic portion comprises PDS II™ or Panacryl™.

31. A bioprosthetic device for soft tissue attachment, reinforcement, and/or reconstruction, the device comprising

a top section of small intestinal submucosa (SIS) including multiple SIS tissue layers each having a surface area, A1,

a bottom section of SIS including multiple SIS tissue layers each having the same surface area, A1, and a mesh device having a surface area, A2, greater than the surface area A1 and being coupled to and positioned to lie between the top and bottom sections of SIS.








FIG. 7




FIG. 8



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 01 30 6559

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	US 3 562 820 A (BRAUN BERNHARD) 16 February 1971 (1971-02-16) * column 1, line 14 - line 30 * * column 2, line 36 - line 46 * * column 4, line 56 - line 69 * ----	1-31	A61L27/36 A61L27/40
X	EP 0 734 736 A (TOYO BOSEKI ;BIO ENG LAB KK (JP)) 2 October 1996 (1996-10-02) * page 2, line 3 - line 14 * * page 5, line 26-48 * * figures 2,4-6 * ----	1	
X	EP 0 466 105 A (CORVITA CORP) 15 January 1992 (1992-01-15) * claim 1 * ----	1	
A,D	WO 00 16822 A (BRIGHAM & WOMENS HOSPITAL) 30 March 2000 (2000-03-30) * claims * -----		
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			A61L
The present search report has been drawn up for all claims			
Place of search <b>THE HAGUE</b>		Date of completion of the search <b>21 November 2001</b>	Examiner <b>Muñoz, M</b>
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ..... & : member of the same patent family, corresponding document	

EPO FORM 1503 03/02 (R04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 30 6559

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

21-11-2001

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
US 3562820	A	16-02-1971	DE	1617330 A1	28-01-1971
			GB	1195992 A	24-06-1970
EP 0734736	A	02-10-1996	JP	2905718 B2	14-06-1999
			JP	8266613 A	15-10-1996
			JP	2905719 B2	14-06-1999
			JP	8266614 A	15-10-1996
			CA	2173508 A1	01-10-1996
			CN	1142975 A	19-02-1997
			EP	0734736 A1	02-10-1996
			US	5876451 A	02-03-1999
			US	5723010 A	03-03-1998
EP 0466105	A	15-01-1992	CA	2045222 A1	13-01-1992
			EP	0466105 A2	15-01-1992
			JP	4242642 A	31-08-1992
WO 0016822	A	30-03-2000	WO	0016822 A1	30-03-2000

EPO FORM P0469

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82